



HOMETEX

Application and Specifications

Application

Ensure that the temperature and relative humidity (RH) of the application space are as close as possible to the given values to achieve the highest product performance. Only work on cool surfaces. Consumption is 80-100 m/m². Surface should be absolutely clean and dry. Ventilate the application area well. Spray on one square meter around 80-100 times with a standard HomeTex bottle until surface becomes slightly wet. Surfaces which do not absorb product should be spread with a cloth slightly. Wait for 24h for drying and curing period. Effect of product can change with respect to fabric type. Make a spot test on hidden part of your fabric. Keep the coated surface away from direct sunlight, dust, water and other contamination during the curing period.

Specifications

Volume	500 ml
Application surface type	Home fabric upholstery
Durability	Up to 6 months
Temperature durability	110°C
Chemical resistance	11>pH>1
Consumption	80-100 ml/m ²
Coating thickness	~75-100 nm
Water repellency	√
Oil repellency	√
Breathability	√
Shelf life	2 years
Keeping conditions	-3°C to +30°C
Curing period	24 h